

## AussieSOL

### AS375R

### Technical Chart 9KT

AS375R is a solder alloy for 9kt red gold. Most suitable applications as below:

- ◆ Cadmium free
- ◆ Low melting point
- ◆ Can be used in torch soldering

#### Physical Characterization Data

COLOR	Red
DENSITY [G/CM <sup>3</sup> ]	10.90
MELTING TEMPERATURE	1030 °C
MINIMUM TEMPERATURE OF WORK	780 °C
ANNEALING TEMPRATURE AND TIME	640 °C for 20 min with a quick cool

#### Notes:-

The above directions are only indicative. Strong variations to the above data are possible, depending on personal experience. Please, do not hesitate to contact us for further information.