



Aussiemet

AussieMech



WM102

Technical Chart 9KT

WM102 is mechanical working master alloy for 9-18kt white gold.
Most suitable applications as below:

- ◆ Can be used in continuous casting
- ◆ Can be used in Wire Production
- ◆ Can be used in Sheet Production
- ◆ Can be used in CNC and Lathe Production
- ◆ Suitable for mechanical working application like stamped items, solid and hollow chains, earrings, bracelets and tube rings

Physical Characterization Data

COLOR	White
DENSITY [G/CM ³]	11.10
MELTING TEMPERATURE	1060 °C
HARDNESS AS CAST	120 HV
HARDNESS (AFTER COLD WORK 70%)	286 HV
HARDNESS (AFTER ANNEALING)	135 HV
HARDNESS (AFTER AGE HARDNING)	135 HV

Mechanical Working Parameters

PRE-MIXING TEMPERATURE [°C]	1050-1140
PICKLING	Sulphuric Acid (%10)

Casting Temperature	Metal - from [°C]	Metal - to [°C]
INGOT MAKING	1070	1110
CONTINUOUS CASTING	1090	1170

Recommended Reductions

SHEET - AREA OR THICKNESS [%]	65
WIRE - DIAMETER [%]	45

Mechanical working recommended annealing	Temperature [°C]	Time [min]
> 5 mm	660 - 680	40
1 - 5 mm	660 - 680	30
< 1 mm	660 - 680	20

Reusing Scrap Instructions

Before reuse of scraps clean the scrap in best possible manner with the ultrasonic and magnetic polishing machine and remove all the dirt, oil, and greases from the metals. The scrap use percentage is not more than 50%.



Hardening Treatment

275°C for 100 minutes cool very slowly possibly inside the furnace with a protection of hydrogen. To obtain further hardening increase the time in the furnace.

Notes:-

The above directions are only indicative. Strong variations to the above data are possible, depending on personal experience. Please, do not hesitate to contact us for further information.



Aussiemet

Website: www.aussiemet.com.au,

Email: info@aussiemet.com.au, sales@aussiemet.com.au,

89 SOMERSBY CIRCUIT, ACACIA GARDENS, NSW 2763, AUSTRALIA